

FLEXO® WRAP

- **Heavy Duty Hook And Loop Closure For Frequent Access**
- **Expands To Fit Over Inline Connectors And Splices**
- **Cut And Abrasion Resistant**
- **Halogen Free**

Put-Ups

Nominal Size	Part #	Hook & Loop Width	Bulk Spool	Shop Spool	Available Colors	Lbs/ 100'
1/2"	FWN0.50	1/4"	100'	20'	4	1.30
3/4"	FWN0.75	5/8"	100'	15'	4	1.80
1 1/4"	FWN1.25	5/8"	100'	12'	4	2.30
2"	FWN2.00	5/8"	100'	10'	4	3.20
2 1/2"	FXN2.50BK	5/8"	100'	10'	BK	3.75




Cut Cleanly
Hot Knife

Flexible, Control & Management With Easy On, Easy Off Access


FLEXO WRAP (FW) is an exclusive product engineered and manufactured by Techflex. FW provides the perfect solution to a wide variety of unique application challenges.

The color matched hook and loop closure provides for easy on and off installation, as well as instant and convenient access for harness break-outs and rework of any specific section along the entire length of the run. Combined with the expandable, open weave design, FW will conform to a wide variety of bundle diameters and will wrap around irregular shapes.

- **Colors Available:**
4 = BK, WH, GY and BE.



- **The large overlap allows easy installation over splices and inline connectors without exposing wires and cables.**



Colors Available:



Black (BK), White (WH), Gray (GY) and Beige (BE).

Material	Polyethylene Terephthalate
Grade	FWN
Monofilament Diameter	.010"
Drawing Number	TF001FWPT-WD



FLEXO® WRAP



Abrasion Resistance
Medium

Abrasion Test Machine
Taber 5150

Abrasion Test Wheel
Calibrase H-18

Abrasion Test Load
500g

Room Temperature
70°F

Humidity
63%

Visible Hole Through
Material Destroyed
900 Test Cycles

Pre-Test Weight
3,772.7 mg

Post-Test Weight
3,391.1 mg

Test End Loss Of Mass
Point Of Destruction
381.6 mg



Rating _____ **UL94V0**



Chemical Resistance


1=No Effect 4=More Affected
 2=Little Effect 5=Severely Affected
 3=Affected

Aromatic Solvents	_____	2
Aliphatic Solvents	_____	1
Chlorinated Solvents	_____	3
Weak Bases	_____	1
Salts	_____	1
Strong Bases	_____	2
Salt Water 0-S-1926	_____	1
Hydraulic Fluid MIL-H-5606	_____	1
Lube Oil MIL-L-7808	_____	1
De-Icing Fluid MIL-A-8243	_____	1
Strong Acids	_____	3
Strong Oxidants	_____	2
Esters/Keytones	_____	1
UV Light	_____	1
Petroleum	_____	1
Fungus ASTM G-21	_____	1
Halogen Free	_____	Yes
RoHS	_____	Yes
SVHC	_____	None

Melt Point
 ASTM D-2117
482°F (250°C)

Maximum Continuous
 MIL-I-23053
257°F (125°C)

Minimum Continuous
-103°F (-75°C)



PHYSICAL PROPERTIES

Monofilament Diameter	_____	.010
<i>ASTM D-204</i>		
Flammability Rating	_____	UL94
Recommended Cutting	_____	Hot Knife
Colors	_____	4
Wall Thickness	_____	.025
Tensile Strength (Yarn)	_____	7.5
<i>ASTM D-2256 Lbs</i>		
Specific Gravity	<i>ASTM D-792</i>	1.38
Moisture Absorption	_____	.1-.2
<i>% ASTM D-570</i>		
Hard Vacuum Data <i>ASTM E-595 at 10-5 torr</i>		
TML	_____	.19
CVCM	_____	.00
WVR	_____	.16
Smoke D-Max	_____	56
<i>ASTM E-662</i>		
Outgassing	_____	Med
Oxygen Index	_____	21
<i>ASTM D-2863</i>		

www.techflex.com