
Opening STATSHIELD® ESD SHIELDING BAG Length (L) Date & Lot Code Printed for QC Traceablility Weld Width (W) Seal



Side Weld Seals 3/8 in. (±0.10)



Mixed Unsortable Plastic Scrap

Mixed unsortable plastic scrap shall contain assorted plastics of multiple grades that are co-extruded, bonded or laminated together which are unsortable into individual grades

Desco's bags are recyclable

Statshield® bags are packaged 100 per package in an oversized shielding bag. Shelf life of bags is minimum one year in normal indoor storage conditions.

STATSHIELD® METAL-OUT SERIES

Specifications:

Electrical Properties Test Procedures/Method **Typical Values** Surface Resistance: Outer Surface <10E8 ohms ANSI/ESD STM11.11 Inner Surface <10E11 ohms ANSI/ESD STM11.11 Static Shielding <25 nJ ANSI/ESD STM11.31, EIA 541 Charge Generation (nC/in²) Teflon: -0.03 Modified Incline Plane Quartz: +0.10 Modified Incline Plane

Capacitance Probe (to dissipate 1 KV) <30 volts ANSI/EIA-541/Appendix E, 1kV Discharge

Physical Properties:

Bag Thickness: Thickness Nominal .0030" (.0762mm) ±10% MIL-STD-3010, 1003 Width (Inside Dimensions) Nominal -0" / + .125" Length (Inside Dimensions) Nominal ± .125" Light Transmission 40% (Tobias) ASTM D-1003 Tensile 9000 PSI ASTM D882 Puncture Resistance >10 lbs MIL-STD-3010, 2065 **MVTR** 0.40 ASTM F-1249 Heat Seal >10 lbs/in. 375°F, 1/2 sec 60 psi Outgassing Pass ASTM E595 Non-corrosive Pass MIL-STD-3010, M3005

Chemical Properties

No effect on aluminum, copper, silver, Sn-Pb coated foil, Corrosion:

stainless steel, low carbon steel

Polycarbonate compatible: Contains no Amines, Amides, or N-Octanoic Acid.

Bag is free of amines, N-octanoic acid, silicones, and heavy metals.

ANSI/ESD S541 Section 6.2 Outside an EPA

"Transportation of sensitive products outside of an EPA shall require packaging that provides:

- 1. Low charge generation
- 2. Dissipative or conductive materials for intimate contact
- 3. A structure that provides electrostatic discharge shielding."

RoHS and REACH Compliance Statement

None of the RoHS restricted materials or REACH substances of very high concern are intentionally added in manufacturing this product. Ref: Directive 2002/95/EC Article 4.1. and Regulation (EC) No. 1907/2006. See Desco Industries Inc. Limited Warranty at Desco.com.

The bag's material meets the required limits of ANSI/ESD S541 per ANSI/ESD S20.20.

Statshield® and Statfree® are Registered Trademarks of Desco Industries Inc.

Specifications and procedures subject to change without notice.

Made in the United States of America

STATSHIELD® BAG, SHIELDING, METAL-OUT CONSTRUCTION, .0030" (.0762mm)

DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com PHONE (909) 627-8178 FAX (909) 627-7449

DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407

PHONE (781) 821-8370 FAX (781) 575-0172

DRAWING NUMBER 13010

DATE: October 2011