

## STATFREE® ESD ULTRA CLEAR BAG

Meets the required limits of ANSI/ESD S20.20, Packaging standard ANSI/ESD S541, and Static Control Bag standard ANSI/ESD S11.4-2012 Level 5.

## Specifications:

| Typical Value  | Test Procedures/Method  |
|--|---|
| $\ge 1 \text{ x } 10^4 \text{ to} < 1 \text{ x } 10^{11} \text{ ohms}$ | per ANSI/ESD STM11.11   |
| -0.10 (nC/in <sup>2</sup> )  | Modified Incline Plane  |
| +0.10 (nC/in <sup>2</sup> )  | Modified Incline Plane  |
|  |   |
| Nominal .0035" (.0889mm) ±10%<br>Nominal -0" / + .125"                 | MIL-STD-3010, 1003  |
|  | ≥ 1 x 10 <sup>4</sup> to < 1 x 10 <sup>11</sup> ohms<br>-0.10 (nC/in <sup>2</sup> )<br>+0.10 (nC/in <sup>2</sup> )<br>Nominal .0035" (.0889mm) ±10% |

Width (Inside Dimensions) Length (Inside Dimensions) Light Transmission Heat Seal Tensile Strength Puncture Res. MVTR 
 Nominal .0035" (.0889mm) ±10%
 MIL-STD-3010, 1003

 Nominal -0" / + .125"
 STM D-1003

 >90 (%)
 STM D-1003

 >8 (lbs/in)
 375年, .75 sec 60 psi

 >5,300 (MD/TD, psi)
 ASTM D-882

 >25 lbs
 MIL-STD-3010, 2065

 0.35
 ASTM F-1249

## **Chemical Properties**

Polycarbonate compatible: Contains no Amines, Amides, or N-Octanoic Acid.

Bag is free of amines, N-octanoic acid, silicones and heavy metals.

## ANSI/ESD S541 section 6.1 Inside an EPA

"Packaging used within an EPA (that satisfies the minimum requirements of ANSI/ESD S20.20) shall be: • Low charge generation

• Dissipative or conductive materials for intimate contact

| 48 GA Polyester<br>Static Dissipative<br>Permastat™ PE  | <b>RoHS 2 and REACH Statement</b><br>None of the RoHS 2 restricted materials or REACH substances of very high conc<br>are intentionally added in manufacturing this product. Ref: European Union Direct<br>Regulation (EC) No. 1907/2006/CE. See Desco Limited Warranty at Desco.com.              | ive 2011/65/EU and |                                     |
|---|--|--------------------|-------------------------------------|
| Mixed Unsortable Plastic Scrap<br>Mixed unsortable plastic scrap shall contain assorted plastics<br>of multiple grades that are co-extruded, bonded or laminated<br>together which are unsortable into individual grades<br>Desco's bags are recyclable | Meets ANSI/ESD S20.20 and Packaging standard ANSI/ESD S541 tested per ANSI/ESI Statshield <sup>®</sup> and Statfree <sup>®</sup> are Registered Trademarks of Desco Industries Inc. See Bag Selection Chart Click <u>HERE</u> .<br>Specifications and procedures subject to change without notice. |                    | Made in the<br>ed States of America |
| Statshield® bags are packaged 100 per package in an oversized shielding bag.  |  |                    |                                     |
| See Shielding Bag Storage at <u>TB-7057</u> .   | STATFREE" ESD ULTRA CLEAR DAG WITH ZIFF  | ER, 10035 (.       | 000911111)                          |
| DECCO   | DESCO WEST: 3651 WALNUT AVE., CHINO, CA 91710 WEB SITE: Desco.com<br>PHONE (909) 627-8178  | DRAWING            | DATE:                               |
| DESCO   | DESCO EAST: ONE COLGATE WAY, CANTON, MA 02021-1407<br>PHONE (781) 821-8370   | NUMBER<br>13880    | October<br>2013                     |

© 2013 DESCO INDUSTRIES INC. Employee Owned

