



## FEATURES:

- Used for kitting and to help organize the workstation
- Durable conductive styrene
- Die-cut drop-in covers available separately
- Reusable, ensuring best value
- Great container for Kanban
- Made in the United States of America

## SPECIFICATIONS:

Property	Typical Value	ASTM
Specific Gravity	1.09	D-792
Tensile Strength	4,200 psi	D-638
Tensile Elongation	40%	D-638
Flexural Modulus	220,000 psi	D-790
Flexural Strength	6,700 psi	D-790
Total/Free Sulfur	<0.15% / <0.004%	
Chlorides	<0.3 PPM	
Outgassing & Corrosivity	Low	
5KV Decay Time	<0.01 sec @ 10% RH	
Surface Resistance	1 x 10 <sup>3</sup> to < 1 x 10 <sup>8</sup> ohms per ANSI/ESD STM11.13	

Item	Size (inches)	Cavity Size (inches)	# of Cavities
<a href="#">39206</a>	10-1/2 x 8-3/4 x 1-1/2	2 x 1-7/8 x 1	12
<a href="#">39201</a>	14-1/2 x 10-1/8 x 1-7/8	3-1/2 x 2-3/4 x 1-1/4	9
<a href="#">39202</a>	14-3/8 x 10-1/8 x 1-3/4	3 x 3 x 1-1/4	12
<a href="#">39208</a>	8-1/8 x 6-5/16 x 1-7/16	3-5/16 x 2-7/16 x 1-1/8	4
<a href="#">39209</a>	9-7/8 x 7-9/16 x 1	3 x 1-1/2 x 1	10
<a href="#">39210</a>	9-7/8 x 7-9/16 x 1	6-1/2 x 1-1/2 x 1	5
<a href="#">39203</a>	Lid for Kitting Tray 39206		
<a href="#">39204</a>	Lid for Kitting Tray 39201		
<a href="#">39205</a>	Lid for Kitting Tray 39202		
<a href="#">39211</a>	Lid for Kitting Tray 39208		
<a href="#">39212</a>	Lid for Kitting Tray 39209 & 39210		

Note: Per Packaging standard ANSI/ESD S541 section 6.1 Inside an EPA "Packaging used within an EPA (that satisfies the minimum requirements of ANSI/ESD S20.20) shall be: 1. Low charge generation, 2. Dissipative or conductive materials for intimate contact."

Tolerances are ± 1/16"

Specifications and procedures are subject to change without notice.

Made in the  
United States of America

## CONDUCTIVE KITTING TRAYS

**PROTEKTIVE PAK**  
13520 MONTE VISTA AVENUE, CHINO, CA 91710  
PHONE (909) 627-2578  
[ProtektivePak.com](http://ProtektivePak.com)

**DRAWING NUMBER**  
39201

**DATE:**  
May  
2013