CAROL. BRAND

SUPER VU-TRON® III



-50°C to +105°C Types SJOOW/SOOW with Integral Flexfill®



In addition to being completely weather-resistant, Super Vu-Tron® III is amazingly crush-resistant. Go ahead, test it out! You can't damage it even by driving a truck over it. Plus, the proprietary, vulcanized jacket material is virtually impossible to tear. And it's impervious to oil, water, ozone and chemicals.

super dependability, lifetime warranted Super Vu-Tron® III has earned its name!

Integral Flexfill® makes the difference—that's because it's extruded into the interstices of the cord instead of a filler material, creating a more compact cord with enhanced crush-resistance and flexibility. Integral Flexfill® also allows for a more consistent convolution-free product appearance, a major factor with rubber cord.

erations need to be addressed.

So twist it, bend it, roast it, freeze it, use it, abuse it! Use Super Vu-Tron® III once, and you'll never trust anything else!



SUPER VU-TRON® III Types SJOOW/ SOOW

-50°Cto +105°C 300 and 600 Volt UL/ CSA Portable Cord



Product Construction:

Conductors:

• 18 through 10 AWG fully annealed stranded bare copper per ASTM B-174

- · Premium grade color coded oil resistant 105°C EPĎM
- · Color Code: See chart below

- Super Vu-Tron® III, yellow
- Temperature range: -50°C to +105°C UL/CSA
- · Voltage rating: 300 volts Type SJOOW 600 volts Type SOOW

Jacket Marking:

• CAROL SUPER VU-TRON® III (SIZE) 105°C (UL) WATER RESISTANT SJÓOW (OR SOOW) CSA (-50°C) FT-1 P-123-103 MSHA-300 (OR 600) VOLT

Applications:

- Machine tools
- · Power tools
- Dockside power applications
- Motor leads
- · Portable machinery
- Cranes
- · Submersible pumps

Features:

- · Excellent flexibility in cold temperatures
- · Lasts longer in flex applications
- Integral Flexfill®
- · Ozone and weather resistant
- · UL Listed and CSA Certified for indoor and outdoor use
- Water resistant
- · Safety colored
- · High heat and flame resistant
- · Resistant to oils, acids and chemicals
- · Excellent abrasion and cut resistant

Industry Approvals:

- UL Flexible Cord ULSubject 62
- CSA Flexible Cord C22.2-49
- MSHA Approved
- OSHA Acceptable
- JC 580

Packaging:

- 250' (76.2 m), 500' (152.4 m), 1000' (304.8 m)
- · Other put-ups available on special order



TYPE SJOOW - 300 VOLT - UL/CSA										
CATALOG	OG NO. OF AWG COND. NOM.INS. THICKNESS			NOMINAL. O.D.		CURRENT	APPROX.	STD.		
	COND.	SIZE	STRAND	INCHES	mm	INCHES	mm	AMPS†	LBS/M'(S)	CTN.
02001	2	18	41/34	0.030	0.76	0.310	7.87	10	55	1000'
02002	3	18	41/34	0.030	0.76	0.320	8.12	10	56	1000'
02003*	4	18	41/34	0.030	0.76	0.345	8.76	7	80	250'
02004	2	16	65/34	0.030	0.76	0.330	8.38	13	68	1000'
02005	3	16	65/34	0.030	0.76	0.350	9.02	13	85	250'
02006	4	16	65/34	0.030	0.76	0.370	9.04	10	95	250'
02007*	2	14	41/30	0.030	0.76	0.370	9.40	18	85	250'
02008	3	14	41/30	0.030	0.76	0.390	9.91	18	110	250'
02009	4	14	41/30	0.030	0.76	0.420	10.67	15	130	250'

TYPE SOOW - 600 VOLT - UL/CSA										
CATALOG			NOM.INS. THICKNESS		NOMINAL. O.D.		CURRENT	APPROX. NET WEIGHT	STD.	
NUMBER	COND.	SIZE	STRAND	INCHES	mm	INCHES	mm	AMPS†	LBS/M'(S)	CTN.
02031*	2	18	41/34	0.030	0.76	0.365	9.27	10	75	250
02032	3	18	41/34	0.030	0.76	0.380	9.65	10	80	250
02033*	4	18	41/34	0.030	0.76	0.400	10.16	7	100	250
02034	2	16	65/34	0.030	0.76	0.370	9.40	13	85	250
02035	3	16	65/34	0.030	0.76	0.400	10.16	13	105	250
02036	4	16	65/34	0.030	0.76	0.425	10.80	10	115	250
02021*	5	16	65/34	0.030	0.76	0.515	13.08	8	150	250
02037*	2	14	41/30	0.045	1.14	0.520	13.21	18	150	250
02038	3	14	41/30	0.045	1.14	0.525	13.34	18	165	250
02039	4	14	41/30	0.045	1.14	0.590	14.99	15	215	250
02022*	5	14	41/30	0.045	1.14	0.675	17.15	12	285	250
02041*	2	12	65/30	0.045	1.14	0.590	14.99	25	200	250
02042	3	12	65/30	0.045	1.14	0.615	15.62	25	230	250
02043	4	12	65/30	0.045	1.14	0.660	16.76	20	275	250
02023*	5	12	65/30	0.045	1.14	0.730	18.54	16	315	250
02045	3	10	104/30	0.045	1.14	0.680	17.27	30	305	250
02046	4	10	104/30	0.045	1.14	0.740	18.80	25	375	250
02024*	5	10	104/30	0.045	1.14	0.825	20.96	20	432	250

COLOR CODE CHART

NO. OF CONDUCTORS	COLOR
2	Black, White
3	Black, White, Green
4	Black, White, Red, Green
5	Black, White, Red, Orange, Green

Top performance in the toughest environments. Volume change (%) of SUPER VU-TRON III after 28 days at room temperature in the following materials:

ACETIC ACID (30%)+ 19.00	LINSEED OI
AMMONIA HYDROXIDE+3.12	LUBE OIL
ASTM 3 OIL+0.26	MILK
BEER+4.42	NITRIC ACII
BLEACH WATER+2.60	SAE 30 OIL
BUTYL ALCOHOL1.82	SKYDROL 5
CORN OIL	SODIUM HY
FORMALDEHYDE+3.38	SULFURIC A
GLYCOL (ANTI-FREEZE)2.60	TOLUENE
HYDROCHLORIC ACID (20%)+10.60	UNLEADED
JP-4+ 10.90	WATER
KEROSENE+ 10.60	

LINSEED OIL	+ 1.04
LUBE OIL	1.82
MILK	+4.16
NITRIC ACID (10%)	+7.29
SAE 30 OIL	1.30
SKYDROL 500	+ 17.10
SODIUM HYDROXIDE.	+10.90
SULFURIC ACID (10%)	+2.34
TOLUENE	+30.20
UNLEADED GAS	+22.10
WATER	+2.86



4 Tesseneer Drive. Highland Heights. KY 41076

BICCGeneral, Carol Brand, Super Vu-Tronlll and Flexfill are trademarks of General Cable Technologies Corporation © 2000 General Cable Technologies Corporation, Highland Heights, KY 41076

OSHA Acceptable
Occupational Safety and Health

Phone: 1.800.243.8020 www.biccgeneral.com

⁺ Green conductor for grounding only.

⁽S) Actual shipping weight may vary.